PVC COMPOUND - AUTOMOBILE

PVC COMPOUND FOR EXTRUSION GRADE

GRADE			PDC - 950 E	PDC - 759 A	PDC - 727
TEST ITEM	TEST METHOD	UNIT			
Hardness	ASTMD 2240	-	80 SHD	72	75
Specific Gravity	ASTMD 792	-	1.5	1.5	1.25
Tensile Strength	ASTMD 638	Kg/Cm Sq.	380	115	160
Elongation	ASTMD 638	%	15	325	320
APPLICATION			Profiles	Soft Profiles	Sleeves

PVC COMPOUND FOR MOULDING GRADE

GRADE			EC - 45 CE	PDC - 984 B	EC - 10 UMF 65
TEST ITEM	TEST METHOD	UNIT			
Hardness	ASTMD 2240	-	52	51	65
Specific Gravity	ASTMD 792	-	1.13	1.15	1.23
Tensile Strength	ASTMD 638	Kg/Cm Sq.	70	80	120
Elongation	ASTMD 638	%	395	400	350
APPLICATION			Handle Gripper	Grommet	Floor Matt